


**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>B32B 31/30, 15/08</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 98/53992</b> <b>(43) International Publication Date:</b> 3 December 1998 (03.12.98)
<b>(21) International Application Number:</b> PCT/US98/10690 <b>(22) International Filing Date:</b> 28 May 1998 (28.05.98) <b>(30) Priority Data:</b> 60/048,354 30 May 1997 (30.05.97) US 60/056,084 27 August 1997 (27.08.97) US 09/082,608 20 May 1998 (20.05.98) US <b>(71) Applicant:</b> KAISER ALUMINUM & CHEMICAL CORPORATION [US/US]; 6177 Sunol Boulevard, Pleasanton, CA 94566 (US). <b>(72) Inventor:</b> AVALOS, James, T.; 3954 Loch Lomand Way, Livermore, CA 94550 (US). <b>(74) Agents:</b> McGARRIGLE, Philip, L.; Kaiser Aluminum & Chemical Corporation, 6177 Sunol Boulevard, Pleasanton, CA 94566 (US) et al.	<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasiã patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>	

**(54) Title:** METHOD FOR COATING ALUMINUM METAL STRIP**(57) Abstract**

In a preferred embodiment, the present invention is an apparatus and a method for coating both surfaces of a continuous processing aluminium strip by extruding thin polymeric film onto the aluminium strip. Generally, the aluminium strip is uncoiled, passed through a preheating unit, two extrusion heads, a post-heater, an air quench, a lubricator, and then it is recoiled.

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## METHOD FOR COATING ALUMINUM METAL STRIP

### Technical Field

The present invention is a method for coating both sides of an aluminum strip by  
5 extruding a thin polymeric film onto the strip.

### Background Art

Currently, thermosetting protective and decorative coatings are generally applied to metal strip or strip for packaging end uses by roller-coating of a solvent-based film. After  
10 application of the film to the metal sheet or strip, the solvent is typically removed by evaporation and the applied coating is cured. The coating can be applied by a variety of processes such as roll coating, reverse roll coating, spraying, electrocoating, powder coating, and lamination. The coated strip may be used in such applications as cans and can ends, foil pouches, lidding stock, appliances, electrical devices, construction,  
15 aerospace or automotive body strip.

The present invention is a new apparatus and process for coating can stock, lid stock, tab stock, and food container stock.

### Brief Description of the Drawings

20 Figure 1 is a schematic view of the device of the present invention.

Figure 2 shows the extruder head.

Figure 3 shows the relationship of the extruder head to the support and pressure rollers.

### Disclosure of the Invention

25 The present invention is a device for extruding a resin coating onto a moving aluminum strip, comprising: a first extrusion coating head for coating one side of the strip, the coating head being capable of applying a thermosettable or thermoplastic resin, the coating head comprising a resin reservoir, an extruder barrel, where the resin is  
30 heated to a low temperature melt point of between 310° F. and 380° F., a slotted die, and a means for extruding the melted resin through the slotted die under pressure; the slotted die is positioned vertically above the strip, which is moving on the support roller, so that the extruded resin is applied to the surface of the strip and compressed when it is

5 moved through the compression roller; a second means for positioning the strip, comprising a support roller and a compression roller, so that the uncoated side of the strip is positioned to accept a resin coating; a second extrusion coating head for coating the uncoated side of the strip, the coating head being capable of applying a thermosettable or thermoplastic resin, the coating head comprising a resin reservoir, an extruder barrel where the resin is heated to a low temperature melt point of between 310° F. and 380° F., a slotted die, and a means for extruding the melted resin through the slotted die under pressure; the slotted die is positioned vertically above the strip, which is moving on the support roller, so that the extruded resin is applied to the surface of the strip and compressed when it is moved through the compression roller; and a resin cure means. The present invention also includes a process for extruding a resin coating onto a moving aluminum strip, comprising: creating a moving aluminum strip; melting a resin at a temperature between 310° F and 380° F; extruding a resin onto at least one side of the moving aluminum strip; curing the resin; and quenching the aluminum strip.

15       Among other things, the present invention is a simplified way to coat both sides of a moving aluminum strip. The resin melts and sets at a lower temperature, which allows the device and process to be smaller and simpler.

20       More specifically, the present invention is a device for extruding a resin coating onto a moving aluminum strip, comprising: an uncoiler; entry rollers; a means to heat the strip; a first means for positioning the strip, comprising a support roller and a compression roller; a first extrusion coating head for coating one side of the strip, the coating head being capable of applying a thermosettable or thermoplastic resin, the coating head comprising a resin reservoir, an extruder barrel, where the resin is heated to a low temperature melt point of between 300° F. and 380° F., a slotted die, and a means for extruding the melted resin through the slotted die under pressure; the slotted die is positioned vertically above the strip, which is moving on the support roller, so that the extruded resin is applied to the surface of the strip and compressed when it is moved through the compression roller; a second means for positioning the strip, comprising a support roller and a compression roller, so that the uncoated side of the strip is positioned to accept a resin coating; a second extrusion coating head for coating the uncoated side of the strip, the coating head being capable of applying a thermosettable or thermoplastic resin, the coating head comprising a resin reservoir, an extruder barrel where the resin is

heated to a low temperature melt point of between 310° F. and 380° F., a slotted die, and a means for extruding the melted resin through the slotted die under pressure; the slotted die is positioned vertically above the strip, which is moving on the support roller, so that the extruded resin is applied to the surface of the strip and compressed when it is moved through the compression roller; a resin cure means; a third means to position the strip; a means to cool the strip, comprising an air quench; a fourth means for positioning the strip; a means to lubricate the coated strip; exit rollers; and a recoiler. The preferred device further comprises a preheat oven which heats the strip to between 365° F. and 400° F., and a curing oven which heats the strip to a temperature between 430° F. and 460° F.. Preferably, the final thickness of the resin coating on the strip is between 0.00004 and 0.0004 inches, and the slot die thickness is between 0.014 and 0.018 inches. The preferred process includes extruding a resin coating onto a moving aluminum strip, comprising: uncoiling an aluminum strip; heating the strip to a temperature between 350° F and 400° F; coating one side of the strip with an extrudable resin that has been heated to a temperature between 325° F and 370° F ; drawing the resin coating to between 0.00004 and 0.0005 inches; positioning the strip to receive a second resin coating; coating a second side of the strip with an extrudable resin that has been heated to a temperature between 325° F and 370° F ; drawing the second resin coating to between 0.00004 and 0.0005 inches; curing the resin coatings on the strip by heating the strip to between 430° F and 460° F; quenching the strip to between 130° F and 150° F; lubricating the strip; and coiling the strip.

#### Best Mode for Carrying out the Invention

In a preferred embodiment, the present invention is an apparatus and a method for coating both sides of a continuous process aluminum strip by extruding thin polymeric film onto the aluminum strip. Preferably, the aluminum strip is uncoiled, passed through a preheating unit, two extrusion heads, a post-heater, a quench, a lubricator, and then it is recoiled.

The present invention is designed to coat an aluminum strip surface with a thin polymeric film. (The polymeric film may also be called a extrudate, resin, or extrusion coating.) The aluminum strip can be produced in a variety of different ways. For example, the strip may be produced according to the methods shown in any of the

following United States patents, which are all incorporated by reference in their entireties: U. S. Patent No. 5,470,405; 5,514,228; 5,515,908; 5,564,491; 5,496,423; and 5,356,495. These patents describe a process for producing an aluminum strip that is about 12 inches wide and is suitable for beverage can manufacture. The aluminum strip is typically coiled and stored in an uncoated state. However, the present invention contemplates obtaining strip from a stored coil or as an in-line process. Equipment for coiling is known in the art and it includes the following types: coil leveling lines, coil annealing lines, coil shearing lines, and coil lithostrip lines. Furthermore, standard coilers operate at speeds from 200 feet per minute to 4000 feet per minute. Additionally, the coilers can operate at temperatures of the aluminum strip between 200°F. and 600°F.

At some point before the strip surface is coated with the resin, it is precleaned or pretreated to provide a better surface for the resin to adhere. Cleaning methods are known to those of skill in the art and include caustic or acid washes. Pretreatments may include chromium, zirconium, or titanium conversion coatings.

A preferred embodiment of the present device is illustrated in Figure 1 and it consists of entry rollers 2 to position the aluminum strip 4, a preheat oven 6, a first extrusion coating head 8 for the bottom surface of the strip 4, rollers 10 to position the aluminum strip 4 relative to the first extrusion coating head 8, a second extrusion coating head 12 for the top surface of the aluminum strip 4, a pair of rollers 14 designed to position the aluminum strip 4 relative to the second extrusion coating head, a final cure heater 16 and a roller 18 to position the aluminum strip 4 as it exits the heater and before it enters an air quench 20, a roller 22 to position the aluminum strip 4 as it leaves the air quench and enters a lubricator, two-roll coater 24, and exit rollers 26 designed to position the aluminum strip 4 relative to the lubricator and the coiler.

The aluminum strip 4 can be uncoiled by methods known in the art. During uncoiling, it is fed into the present process and apparatus for extrusion coating. The present extrusion coating device is operated in an in-line process as follows. Several rollers may be positioned before rolls 2 and after rolls 26 in the present device to ensure appropriate positioning of the moving aluminum strip 4. The first portion of the present device is a preheat portion 6, preferably an induction heater or an infrared heater. Other methods for heating a moving aluminum strip 4 are known in the art and they include the following: air-gas convection; infrared; plasma; and corona discharge heaters.

The preferred moving aluminum strip 4 is typically between 0.006 and 0.015 inches in thickness, more preferably between 0.008 and 0.012 inches in thickness. Preferably, the strip is at least 4 or 6 inches wide, more preferably, at least 8 or 10 inches wide. Preferably, the strip is no more than 36 or 24 inches wide, more preferably, no  
5 more than 20 or 12 inches wide. Consequently, a heater must be able to provide the appropriate heating capability to this type of material.

The moving aluminum strip 4 can be uncoiled at a rate of between 200 and 4000 feet per minute, most preferably between 800 and 1200 feet per minute.

The preheat oven 6 preferably heats the moving aluminum strip 4 to a  
10 temperature above 350° F., but not more than 400° F. More preferably, the oven 6 heats the moving aluminum strip 4 to above 365° F., but less than 390° F.

An extruder head 28 is shown in Figure 2 and is comprised of a single screw, slot die extruder for extruding a thin polymeric film onto at least one surface of the aluminum strip. It contains a hopper or reservoir 30 for loading resin pellets, which leads to an  
15 extruder barrel 32 where the pellets are heated to a low temperature melt point of not more than 380° F. or not less than 310° F., more preferably not more than 370° F., and not less than 325° F. Inside the extruder barrel, a rotating screw forces the melted resin through a transfer bar 34 and a feeding block 36. The rotating screw is driven by a motor and armature 38 and preferably generates 2000 lbs pressure to extrude the resin.

20 The primary purpose of the slot die 40 is to define a width and to provide an even cross sectional film thickness as well as smoothness of the extruded film. The preferred die design is based on the hinge effect, allowing smooth, precise adjustments on relative narrow center lines.

A slot die 40 is positioned in the feeding block so that the film exits in a form of a  
25 thin curtain. The slot die 40 preferably extends 3/4 of an inch on each side of the strip width, but not more than 1 inch. Preferably, the slot die aperture 42 is at least 0.012 inches wide, preferably, not more than 0.025 inches wide. More preferably, the slot die aperture 42 is at least 0.014 inches wide, preferably, not more than 0.020 inches wide. The preferred die is hinged to allow adjustments to be made in the width of the die  
30 opening. Preferably, the width can be adjusted every 1 1/2 to 2 1/2 inches along the length of the die, more preferably, every 2 inches.

The film thickness can be measured by a micrometer after it has been extruded

and allowed to come to room temperature. Also, the film thickness can be measured as it is applied to the strip by using a device that measures the capacitance as compared to standards. Thereafter, the die may be adjusted to vary the film thickness.

5 The slot die 40 is preferably positioned just over the nip of two polymer-coated steel rolls. (The moving strip travels in the direction of the arrow shown in Fig. 2.). The two rollers are a support roller 44 and a pressure roller 46. Horizontal or vertical extruders can be used with, or without the feeding block arrangement. The polymer coated steel rolls are made of a high-temperature-resistant silicon-type polymer of between 35 and 50 durometer hardness. Figure 3 shows the positioning of the slot die 40  
10 relative to the aluminum strip 4 and the two rollers 44, 46. The two rollers comprise a support roller 44 and a compression roller 46, also known as a nip pressure roller. The vertical offset 50 between the centers of both rolls 44, 46 is designed to reduce the air gap and reduce the air entrapment. Preferable, the centers of each roll are substantially vertically offset by about 1 inch to about 1 1/2 inches, more preferably the distance is  
15 between 1 1/8 and 1 1/4 inches. The slot die 40 in the extruder head 28 is positioned between 1/8 to 1 inches above the aluminum strip 4, more preferably approximately 3/8 of an inch. The slot die 10 is positioned approximately between 1-5/8 and 2-1/4 inches, more preferably approximately 2 inches from the center of the support roll 44 towards the compression roll 46 (see 52). It can be understood by one of ordinary skill in the art  
20 that the gap between the slot die 40 and the support roll 44, the speed of the aluminum strip 4, and the resin amount are proportioned so that the resin does not overcoat the aluminum strip 4. A modification in one of the elements above may necessitate a modification in another of the above elements. Such modifications are within the skill of the art. The compression roller 46 is used to draw the thin resin and to remove air.

25 The nip pressure roll 46 is designed so that it does not pick up any resin. These rolls are preferably covered with a silicone type polymer which provides release of the extruded films. This is an inherent property of silicone, it is incompatible with other resins, it only adheres to itself. The support roll 46 and the nip pressure roll 44 are also designed to be opened and closed. For example, the two rollers can be pulled apart for  
30 positioning of the strip 4 or other operations. Preferably, the distance between the centers of the rolls is 6-3/8 inches when opened, and 5-7/8 inches when closed. These rolls have given favorable performance in that: they provide a good pressure nip for the



bonding of the resin to the moving aluminum strip; the extrudates do not adhere to the pressure roll surface, even at high pressure there is no evidence of the extruded film picking onto the roll surface; they eliminate air entrapment between the extrudate and the aluminum strip; they provide good drawing and polishing of the extruded film; and they exhibit excellent process temperature resistance.

The nip and support roller for the first extrusion coating head 8 of Figure 1 are positioned to coat one surface of the aluminum strip, e.g. the underside of the aluminum strip. The nip and support roller 14 of the second extrusion coating head 12 are positioned to coat the other surface of the aluminum strip, e.g. the top of the aluminum strip in the same manner as the first extrusion coating head 8 applied film to the bottom of the strip. This operation is sequential, in that the first extrusion coating head 8 applies resin 'upstream' of the second extrusion coating head 12.

The resin from the extrusion coater is applied to the aluminum strip in a certain thickness. For example, it is preferred that the resin is extruded at no more than 0.018 inches thick, but not less than 0.005 inches thick, more preferably no more than 0.016 inches thick, but less than 0.01 inches thick. Typically, the extrusion coating is drawn to a reduced thickness of approximately no more than 0.0004 inches thick, and no less than 0.00004 inches thick. More preferably, not more than 0.0003 inches thick, and not less than 0.00003 inches thick. The extrusion coating may be drawn by the pressure of the compression roller, for example. Other methods of drawing are through the modification of the aluminum strip speed and the nip roll pressure.

After the aluminum strip 4 is moved from the second extrusion coating head 12 and its two rollers 14, it is fed to the final cure, such as an infrared or induction heater 16, to dry or cure the resin. Typical heaters of this type include: air-gas convection; infrared; plasma; and corona discharge heaters. This heater 16 also can be called a curing oven. The temperature to which the aluminum strip 4 is heated is preferably no more than 460° F., but no less than 430° F. More preferably the aluminum strip is heated to no more than 450° F., but no less than 440° F.

The moving aluminum strip 4 is passed to a quench 20, preferably an air quench, also called an air flotation cooler. Air quenching is designed to cool the moving aluminum strip 4 with the applied resin so that it can be lubricated and recoiled. Air quench devices are commonly known in the art. Other quenching/cooling devices

include: cooling drum rolls; water quench; and/or a combination of air-water quenching.

Preferably, the moving aluminum strip 4 is cooled to no more than 150° F., more preferably to no more than 130° F. To achieve cooling to these temperatures, the air quench is adapted to provide air flows of approximately 1200 feet per minute.

5 After passage through the air quench, the aluminum strip 4 is positioned using a roller 22 into a two roll (per side) coat lubricator 24. These lubricators 24 are known in the art and are commercially available. Representative examples of this type of device are: air spray; and electrostatic lubricators.

This lubricator 24 will apply a lubricant, such as a microcrystalline wax or light  
10 oil. This lubrication serves a purpose of lubricating the aluminum strip 4 for further can making operations such as cupping and body making (in the case of can body stock), or formation into the lid or tab for lid and tab stock.

The aluminum strip that is coated by this invention may be a variety of alloys and tempers, depending on the use of the strip. The strip is preferably greater than 4 or 6  
15 inches wide, more preferably, more than 10 or 12 inches wide. Preferably, the width of the strip is not more than 36 or 24 inches wide, more preferably no more than 20 or 18 inches wide.

Typical aluminum alloys are used as can body stock, lid and tab stock. In general, alloys suitable for use in the practice of the present invention are those aluminum alloys  
20 containing from about 0 to about 0.6% by weight silicon, from 0 to about 0.8% by weight iron, from about 0 to about 0.6% by weight copper, from about 0.2 to about 1.5% by weight manganese, from about 0.2 to about 5% by weight magnesium, from about 0 to about 0.25% by weight zinc, with the balance being aluminum with its usual impurities. Representative of suitable alloys include aluminum alloys from the 1000,  
25 2000, 3000, 4000, 5000, 6000, 7000, and 8000 series. Some examples are the 3000 and 5000 series, such as AA 3004, AA 3104, AA 5017, and 5182.

Typical tempers are the H-19 or H-39 tempers and the metal strip is typically 0.1778-0.356 mm (0.007 to 0.014 inches) thick.

Other devices used for coating surfaces of aluminum strip are shown in the  
30 following U.S. patents: 5,407,702; 5,582,319; and 5,197,536 as well as PCT Publication WO 94/01224, the disclosures of which are all hereby incorporated by reference in their entireties.

In accordance with this invention, a variety of thermoplastic or thermosettable polyester resins can be used to coat an aluminum strip which is designed for use in packaging, such as can bodies, can lids or tabs. PCT publication WO 94/01224 provides a description of many resins that are used to coat aluminum can stock. The disclosure of  
5 this PCT application is hereby incorporated by reference in its entirety. Thermoplastic resins suitable for use in this invention include polypropylene, polyethylene, polyamides (nylon), polycarbonates, and polyvinyl chloride (PVC) and epoxies. A highly preferred resin is Dow Primacor® 3460 polymer, which is an ethylene-acrylic acid copolymer.

The composition may, for example, comprise one of the following systems, or a  
10 blend of two or more such systems may be used:

- 1) Epoxy resin, or epoxy novolac resin, preferably, but not limited to, bisphenol Apichlorohydrin-based materials exemplified by solid materials such as, for instance, Shell Epikote 1009, 1007, 1004, 1002, 1001 and 828, in combination with one or more resole phenolic resins which may be alkylated or non-alkylated  
15 as exemplified by Uravar FB190, Uravar FB120, Varcum 29-101, Varcum 29-108, Varcum 29-159, Varcum 29-183 and Varcum 94-635.

The epoxy resin may be modified with one or more polyesters, which may be branched or linear, acid- and/or hydroxy-functional, as exemplified by Dynapol  
20 LH820 (a saturated, medium molecular weight, linear, hydroxy-functional polyester); Dynapol L858 (a saturated, high molecular weight, branched polyester); Dynapol L206, (a saturated, high molecular weight, linear polyester); and Uralac 2695 (a saturated, medium molecular weight, branched carboxylated polyester); or (b) one or more diacids, exemplified by succinic, adipic, sebacic,  
25 isophthalic, terephthalic and phthalic acids or © one or more diols exemplified by ethylene, propylene, diethylene and triethylene glycols, 1,4-butanediol, 1,6-hexanediol, and cyclohexanedimethanol.

The system may be further crosslinked with one or more essentially solvent-free  
30 aminoplast resins, exemplified by Cymel 301 (hexamethoxymethyl melamine), Cymel 1123 (Benzoguanamine formaldehyde), Cymel 1170 (Glycol uril formaldehyde) and UFR-80 (Urea formaldehyde), all from Dyno Cynamid, and/or

bisphenol A epichlorohydrin-based epoxy resins, exemplified by liquid materials such as, for instance, Shell Epikote 828, Dow DER330, Ciba Araldite GY2600 and 260, and/or epoxy novolac resins exemplified by Dow DEN 431 or DEN 438.

- 5      2) Polyester resin, as exemplified by those described in 1)a) above, in combination with one or more resole phenolic resins as exemplified by those described in 1) above, and/or essentially solvent-free aminoplast resins, as exemplified by those described in 1) above. The system may be further crosslinked with additions of epoxy (e.g. liquid epoxy) and/or epoxy novolac resins as exemplified by those described in 1) above.
- 10
- 3) Epoxy resin, as exemplified by materials such as those described in 1) above, in combination with one or more organic anhydrides or anhydride oligomers as exemplified by one or more of trimellitic, succinic, phthalic, hexahydrophthalic and tetrahydrophthalic anhydrides.
- 15
- 4) Epoxy resin, as exemplified by materials such as those described in 1) above, in combination with high solids, typically at least 60 percent, acid-functional acrylic polymers, acid value typically greater than 50 mg KOH/g as exemplified by Reichold Synthemal 40-462, McWhorter Acrylamac 7555, HiTek CMD 979, HiTek RGX-87425, Paraloid AT-70, or Paraloid AT-85.
- 20
- 5) Hydroxy-functional polyester, as exemplified by those described in 1) above, in combination with isocyanate which may be internally or externally blocked as exemplified by uret diones, phenol blocked isocyanates, such as for instance, Desmodur AP stable (Byer), and/or essentially solvent-free aminoplast resin as described in 1) above,
- 25
- 6) (a) Emulsion polymers based on crosslinkable thermosetting acrylic resins, as exemplified by Union Carbide Ucar 4510 and Rohm & Haas Primal AC1822, crosslinked with additional components such as essentially solvent-free aminoplast resins, liquid or solid epoxy resins or epoxy-novolac resins, all as described in 1)
- 30

above.

b) Emulsion polymers based on self-crosslinking thermosetting acrylic resins, as exemplified by Rhoplex AC-604, AC-625, AC 1230 and HA-16.

5

- 7) A linear or branched polyester with acid functionality sufficient for reaction with the chosen crosslinking agent, which may be an epoxy resin, more especially an epoxy resin as described in 1) above. Typically, the polyester will have an acid value of at least 30 mg KOH/g as exemplified by EMS Grilesta V72/6 and Uralac P2695.

10

The system may be crosslinked with dicyandiamide, epoxy-novolac, phenolic and/or aminoplast resins as described in 1) and 2) above.

15

The present device and process will now be illustrated by reference to the following examples which set forth particularly advantageous embodiments. However, it should be noted that these embodiments are illustrative and are not to be construed as restricting the invention in any way.

20

#### Example I

I coated both surfaces of a moving aluminum strip, having the following dimensions 0.0088 gauge by 6 inch width and 1800 linear feet, using the above described extrusion device. The extrudable resin was Vermicolor (manufactured by Dexter Coatings, resin ID no. 96-605-15). The process conditions were:

25

Extruder Parameters:

30

Barrel Temperature	410° F., 420° F., and 430° F.
Transfer Bar	425° F.
Feed Block	400° F.
Die	400° F.
Melt Temperature	370° F.
Feeding Rate	50 RPM exterior surface 60 RPM interior surface

Pressure 1400 -2000  
Line Process Speed 125 f.p.m. for exterior surface  
and 75 f.p.m. for interior surface  
5 Preheat Temperature 350° F  
Cure Temperature 430° F  
Substrate:  
0.0088" x 6" x 5182 x 1800 linear feet chemically and  
conversion coated with zirconium pretreatment.  
10 Applied Film Thickness:  
Interior surface 8 microns; exterior surface 4 microns  
Film Appearance:  
Acceptable clarity and gloss development upon thermal cure  
of 430° F  
15 Film Adhesion:  
Excellent, with no tape removal or feathering after a 15  
minute boiling water immersion test. No apparent blush on  
the coated film after this water-immersion test.  
Retortability (90 minutes at 250° F.)  
20 No apparent blush of the film in either the water or steam  
phase and no loss of adhesion.  
Beverage End Fabrication:  
Beverage, soft drink 202 ends were converted in a  
commercial end production plant. The ends from the  
25 extrusion coated test coil are comparable to the commercial  
ends being produced at the same time. The cut edge is clear  
with no hairing, the extruded film exhibits no flaking or  
fracturing in the countersink or rivet area of the converted  
ends.  
30  
Metal exposure on these fully converted ends was determined by means of  
Enamel Rater test expressed in mil-amp.

		Actual Readings
	Random Test End	Mil-Amp.
5	1	0.1
	2	0.1
	3	0
	4	0.1
	5	0
10	6	0
	7	0
	8	0
	9	0
	10	0

#### Example II

15 To distinguish the present invention from previous processes I tested a resin that is disclosed as a preferred high melt viscosity polyester resin in U. S. Patent No. 5,407,702 and named DuPont Selar® resin PT-8307. I attempted to extrude this resin at a barrel temperature of 450-515 °F, a transfer bar temperature of 530-535 °F, a feed block temperature of 535 °F, an extruding die temperature of 535 °F, and a melt

20 temperature of 480-500 °F. These temperatures were in the recommended range for this resin and they differ substantially from the temperatures recommended for the present process and device as shown above. However, even at these elevated temperatures, I was unable to extrude this resin in the present device due to the high melt viscosity of the resin.

25 The present invention has been described with referenced to specific embodiments. However, this application is intended to cover those changes and substitutions which may be made by those skilled in the art without departing from the spirit and scope of the appended claims.

What is claimed is:

1. A device for extruding a thermoplastic or thermostable polymeric resin coating onto a moving aluminum strip, comprising:  
a first resin extrusion means vertically positioned over one surface of a moving strip, a  
5 means for presenting the other surface of the moving strip, a second resin extrusion  
means vertically positioned over the other surface of the moving strip, wherein a resin is  
melted at a temperature between 310° F. and 380° F. and extruded onto the moving  
strip, a means for positioning the strip surface relative to the extrusion means, means for  
supporting the strip, and a means for compressing the extruded film onto the strip  
10 surface.
2. A device for extruding a resin in accordance with claim 1 wherein the strip is  
between 4 and 36 inches wide.
- 15 3. A device for extruding a resin in accordance with claim 1 wherein the strip is  
between 6 and 24 inches wide.
4. A device for extruding a resin in accordance with claim 1 wherein the strip is  
between 12 and 20 inches wide.
- 20 5. A device for extruding a resin coating onto a moving aluminum strip, comprising:  
a first extrusion coating head for coating one surface of a strip, the coating head  
being capable of applying a thermosettable or thermoplastic resin, the coating head  
comprising a resin reservoir, an extruder barrel, where the resin is heated to a low  
25 temperature melt point of between 310° F. and 380° F., a slotted die, and a means for  
extruding the melted resin through the slotted die under pressure;  
a means for positioning the strip, comprising a support roller and a compression  
roller,  
the slotted die is positioned vertically above the strip, which is moving on the  
30 support roller, so that the extruded resin is applied to the surface of the strip and is  
compressed when it is moved through the compression roller;  
a second means for positioning the strip, comprising a support roller and a



compression roller, so that the uncoated surface of the strip is positioned to accept a resin coating;

5 a second extrusion coating head for coating the uncoated surface of the strip, the coating head being capable of applying a thermosettable or thermoplastic resin, the coating head comprising a resin reservoir, an extruder barrel where the resin is heated to a low temperature melt point of between 310° F. and 380° F., a slotted die, and a means for extruding the melted resin through the slotted die under pressure;

10 the slotted die is positioned vertically above the strip, which is moving on the support roller, so that the extruded resin is applied to the surface of the strip and compressed when it is moved through the compression roller; and  
a resin cure means.

15 6. A device as shown in accordance with claim 5 further comprising a preheat oven which heats the strip to between 365°F. and 400° F.

7. A device as shown in accordance with claim 5 further comprising a curing oven which heats the strip to a temperature between 430° F. and 460° F..

20 8. A device as shown in accordance with claim 5 wherein the final thickness of the resin coating on the strip is between 0.0004 and 0.00004 inches.

9. A device as shown in accordance with claim 5 wherein the slotted die thickness is between 0.012 and 0.018 inches.

25 10. A device for extruding a resin in accordance with claim 5 wherein the strip is between 4 and 36 inches wide.

11. A device for extruding a resin in accordance with claim 5 wherein the strip is between 6 and 24 inches wide.

30 12. A device for extruding a resin in accordance with claim 5 wherein the strip is between 12 and 20 inches wide.

13. A device for extruding a resin coating onto a moving aluminum strip, comprising:  
an uncoiler;  
entry rollers;  
a means to heat a strip;
- 5 a first means for positioning the strip, comprising a support roller and a compression roller;  
a first extrusion coating head for coating one surface of the strip, the coating head being capable of applying a thermosettable or thermoplastic resin, the coating head comprising a resin reservoir, an extruder barrel, where the resin is heated to a low  
10 temperature melt point of between 310° F. and 380° F., a slotted die, and a means for extruding the melted resin through the slotted die under pressure;  
the slotted die is positioned vertically above the strip, which is moving on the support roller, so that the extruded resin is applied to the surface of the strip and compressed when it is moved through the compression roller;
- 15 a second means for positioning the strip, comprising a support roller and a compression roller, so that the uncoated surface of the strip is positioned to accept a resin coating;  
a second extrusion coating head for coating the uncoated surface of the strip, the coating head being capable of applying a thermosettable or thermoplastic resin, the  
20 coating head comprising a resin reservoir, an extruder barrel where the resin is heated to a low temperature melt point of between 310° F. and 380° F., a slotted die, and a means for extruding the melted resin through the slotted die under pressure;  
the slotted die is positioned vertically above the strip, which is moving on the support roller, so that the extruded resin is applied to the surface of the strip and  
25 compressed when it is moved through the compression roller;  
a resin cure means;  
a third means to position the strip;  
a means to cool the strip, comprising an air quench;  
a fourth means for positioning the strip;  
30 a means to lubricate the coated strip;  
exit rollers; and  
a recoiler.

14. A device for extruding a resin in accordance with claim 13 wherein the strip is between 4 and 36 inches wide.
15. A device for extruding a resin in accordance with claim 13 wherein the strip is between 6 and 24 inches wide.
16. A device for extruding a resin in accordance with claim 13 wherein the strip is between 12 and 20 inches wide.
17. A device for extruding a resin in accordance with claim 13 further comprising a preheat oven which heats the strip to between 365° F. and 400° F.
18. A device as shown in accordance with claim 13 further comprising a curing oven heats the strip to a temperature between 430° F. and 460° F.
19. A device as shown in accordance with claim 13 wherein the final thickness of the resin coating on the strip is between 0.00004 and 0.0004 inches.
20. A device as shown in accordance with claim 13 wherein the slot die thickness is between 0.012 and 0.018 inches.
21. A process for extruding a resin coating onto a moving aluminum strip, comprising:
- creating a moving aluminum strip;
  - melting a resin at a temperature between 310° F and 380° F;
  - extruding a resin onto at least one surface of the moving aluminum strip;
  - curing the resin; and
  - quenching the aluminum strip.
22. A process in accordance with claim 21 further comprising repositioning the strip and extruding the resin onto the uncovered surface of the strip.

23. A process for extruding a resin in accordance with claim 21 wherein the strip is between 4 and 36 inches wide.
24. A process for extruding a resin in accordance with claim 21 wherein the strip is  
5 between 6 and 24 inches wide.
25. A process for extruding a resin in accordance with claim 21 wherein the strip is between 12 and 20 inches wide.
- 10 26. A process in accordance with claim 21 wherein the moving aluminum strip is created by uncoiling a strip of aluminum, the resin is cured by a heater, and the strip is quenched using an air cooler.
27. A process in accordance with claim 21 wherein the resin is melted at a  
15 temperature between 325° F and 370 ° F.
28. A process in accordance with claim 21 further comprising heating the moving aluminum strip to a temperature between 350° F. and 400° F. before the strip is coated by the resin.  
20
29. A process for extruding a resin coating onto a moving aluminum strip, comprising:  
uncoiling an aluminum strip;  
heating the strip to a temperature between 350° F and 400 ° F;  
25 vertically extruding a resin that has been heated to a temperature between 325° F and 370° F onto one surface of the strip;  
drawing the resin coating to between 0.00004 and 0.0005 inches;  
positioning the strip to receive a second resin coating;  
vertically extruding a resin onto the other surface of the strip, the resin has been  
30 heated to a temperature between 325° F and 370° F;  
drawing the second resin coating to between 0.00004 and 0.0005 inches;  
curing the resin coatings on the strip by heating the strip to between 430° F and

460° F;

quenching the strip to between 130° F and 150° F;

lubricating the strip; and

coiling the strip.

5

30. A process for extruding a resin in accordance with claim 29 wherein the strip is between 4 and 36 inches wide.

31. A process for extruding a resin in accordance with claim 29 wherein the strip is  
10 between 6 and 24 inches wide.

32. A process for extruding a resin in accordance with claim 29 wherein the strip is between 12 and 20 inches wide.

1/3




FIG. 1/3

2/3





FIG. 2/3

3/3





# INTERNATIONAL SEARCH REPORT

Int. l. Application No

PCT/US 98/10690

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 B32B31/30 B32B15/08

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B32B B05D B05C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 96 32202 A (ALUMINUM COMPANY OF AMERICA) 17 October 1996	1-12
Y	see claims 1,8,13,15,36-38	13-20, 22-32
	---	
X	WO 94 01224 A (COURTAULDS COATINGS (HOLDINGS) LIMITED) 20 January 1994	21
	cited in the application	
Y	see claim 1; examples 5,6A,6B	22-32
	---	
Y	US 3 832 962 A (ROLF ROLLES) 3 September 1974	13-20
	see column 2, line 49 - line 64; example 6	
	---	
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

1 September 1998

Date of mailing of the international search report

07/09/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Van Nieuwenhuize, O

# INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 98/10690

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	PATENT ABSTRACTS OF JAPAN vol. 005, no. 079 (C-056), 23 May 1981 & JP 56 026568 A (SHOWA ALUM CORP), 14 March 1981 see abstract ---	13-20
Y	PATENT ABSTRACTS OF JAPAN vol. 005, no. 016 (C-041), 30 January 1981 & JP 55 144098 A (SHOWA ALUM CORP), 10 November 1980 see abstract ---	13-20
Y	PATENT ABSTRACTS OF JAPAN vol. 013, no. 465 (M-882), 20 October 1989 & JP 01 182248 A (TOYO SEIKAN KAISHA LTD), 20 July 1989 see abstract ---	13-20
P,X	WO 97 44394 A (JUNG ROLF ;WIDMER HANS (CH); SCHMID CHRISTIAN (CH); DEXTER CORP (U) 27 November 1997 see page 39, paragraph 2 - page 40, paragraph 2; claim 3; examples 1,2,6,8,9 ---	21
A	WO 96 20086 A (SMS SCHLOEMANN-SIEMAG AKTIENGESELLSCHAFT) 4 July 1996 see claims 1-3; figure 1 ---	1-32
A	US 3 616 020 A (MARK W. WHELAN ET AL) 26 October 1971 see figure 2 ---	1,5
A	EP 0 067 060 A (TAYO STEEL CO., LTD.) 15 December 1982 see figure 3 ---	1,21
A	PATENT ABSTRACTS OF JAPAN vol. 4, no. 22 (C-074), 23 February 1980 & JP 54 158448 A (ASAHI CHEM IND CO LTD), 14 December 1979 see abstract; figure 2 ---	1,21
A	US 5 225 249 A (GIRMA BIRESAW ET AL) 6 July 1993 see the whole document -----	13

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/10690

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9632202 A	17-10-1996	EP 0820353 A	28-01-1998
WO 9401224 A	20-01-1994	AU 688731 B	19-03-1998
		AU 4510493 A	31-01-1994
		EP 0648150 A	19-04-1995
		JP 7509175 T	12-10-1995
		NZ 253770 A	28-10-1996
		SG 46234 A	20-02-1998
		US 5639514 A	17-06-1997
US 3832962 A	03-09-1974	NONE	
WO 9744394 A	27-11-1997	AU 3069897 A	09-12-1997
WO 9620086 A	04-07-1996	DE 19535680 A	27-06-1996
US 3616020 A	26-10-1971	BE 763577 A	16-07-1971
		CA 973131 A	19-08-1975
		DE 2109652 A	07-09-1972
		DE 2163997 A	27-07-1972
		FR 2126106 A	06-10-1972
		FR 2120064 A	11-08-1972
		GB 1348271 A	13-03-1974
		NL 7102123 A	21-08-1972
		US 3854612 A	17-12-1974
EP 67060 A	15-12-1982	JP 1680842 C	13-07-1992
		JP 3041342 B	21-06-1991
		JP 57203545 A	13-12-1982
US 5225249 A	06-07-1993	NONE	